

**TABLE 3
 ASBESTOS SAMPLE SUMMARY
 SELECTED GOW BUILDING REMNANTS
 UMORE PARK
 ROSEMOUNT, MINNESOTA**

| Sample ID | Matrix | Asbestos Result |
|-----------------------|------------------------------|------------------|
| TT-30-1(Surface)-234H | insulation | 15% |
| TT-30-2(Surface)-234H | black tar | ND |
| TT-30-3(Surface)-234H | tar paper | 40% |
| TT-40(0-1')-214C-13 | black mastic | 45% |
| TT-41(6")-269B | wallboard | 35% |
| TT-63(Surface)-220C | red mastic | ND |
| TT-70-1(0-1")-239A | black mastic on chicken wire | Approximately 1% |
| TT-70-2(0-1")-239A | tan transite | 35% |
| TT-70-3(0-1")-239A | black mastic | 3% |
| TT-70-4(0-1")-239A | brown transite | 40% |
| TT-70-5(0-1")-239A | gray transite | 40% |
| TT-71-1(Surface)-238B | red mastic | Approximately 1% |
| TT-72-1(Surface)-237K | red mastic | 3% |
| TT-72-2(Surface)-237K | corrugated transite | 20% |
| TT-72-3(Surface)-237K | gray flat transite | 40% |
| CS-6-106B(105B) | black mastic | ND |
| CS-7-1-106B | black mastic | 20% |
| CS-18-2-109B | black mastic | ND |
| CS-24-1-113B | white wallboard | ND |
| CS-29-2-208C | white wallboard | 40% |
| CS-36-1-233A | black mastic on chicken wire | 15% |
| CS-37-1-209A | red mastic | 5% |
| CS-43-2-234H | red mastic | Approximately 1% |
| CS-48-2-214C-13 | black mastic on chicken wire | Approximately 1% |
| CS-48-3-214C-13 | white wallboard | 40% |
| CS-55-2-239A | black mastic | 2% |
| CS-56-2-238B | red mastic | 3% |
| CS-62-2-236B | black mastic | 16% |